



ETIC CERAMICS

DATA SHEET OF CERAMIC FOAMS

Specification

Item	Unit	Value
Bulk density	kg/m ³	150—400
Anti-acid	%	99.92
Anti-alkai	%	98.26
Rupture strength	MPa	1.2—2.2
Crush strength	MPa	2.1—4.6
Liner expansion	/°C (0—500°C)	5.6×10^{-6}
Water absorption	%	≤3
Operating temp.	°C	-40 ~ +400
Flamable		No flamable

Dimension

Item No	Dimension(WXLXH,mm)
EB01	150×225×50
EB02	120×240×50
EB03	150×225×65
EB04	120×240×65